

# FINISH FILLER

READY TO USE

## FILLER FOR SURFACE FINISHING

- ◆ **EASY TO SAND**
- ◆ **EXCELLENT FINISH**
- ◆ **NO NEED TO SPOT PRIME**
- ◆ **SMOOTH APPLICATION**



### PURPOSE

Ready ready to use finishing surface filler for plasterboard.

### SUBSTRATES

Finish Filler can be applied on gypsum, old painted surfaces, cement, concrete, cellular concretend any type of butted or tapered plasterboard.

### OVERCOATING

Finish Filler can be coated with any type of primer or surface filler.

### PHYSICAL AND TECHNICAL FEATURES

- Finish Filler: in ready mixed form for interior use, made of mineral components and synthetic resin.
- Characterisation (NFT 36-005): Family III - Class 2.
- Codification (EN 16566):  $G_3S_1V_0W_0A_0C_0R_0$ .
- Mixing rate: ready to use.
- Application thickness: up to 5 mm.
- Coverage: 1.7 kg/m<sup>2</sup>/mm.
- Setting time: second coat as soon as the filler is hard and dry to the touch.
- Overcoating: can be painted in 12 to 24 hours average time (after complete drying).
- Colour: white.
- Adhesion: filler/substrate (EN 16566): > 0.5 Mpa.

### USE AND STORAGE CONDITIONS

- Application tools: filling or taping knife, trowel, blade. This product can be sprayed.
- Tool cleaning: after use, product residue can be rubbed off tools when dry (water cleaning is not necessary).
- Preservation: product guaranteed 12 months. Stored away from sunlight and frost.  
If found to be faulty within the guarantee period, we willl arrange a replacement on proof of purchase.

### PACKAGING

- Bucket: 20kg.

### RECOMMENDATIONS AND CARE FOR USE

The times mentioned are indicative and depend on the substrate, coat thickness, and the ambient conditions.

Do not apply at a temperature below 8°C or above 35°C nor at a relative humidity over 70%.

Do not apply on overheated surfaces or damp substrates.

Do not apply on polystyrene, nor on wall paper, nor on exterior substrates.

### SUBSTRATES PREPARATION

Substrates to be prepared as per the current trade practices.

Substrates must be hard, cohesive, clean, sound and dry.

### NORMATIVE DOCUMENTS TO BE REFERRED TO

- NFT 36-005: Characterisation of paint products.
- NF/BS EN 16566:2014 (Paints and varnishes. Coatings Fillers for internal and/or external works).
- NF/BS EN 13963:2014 (Jointing materials for gypsum boards).

### HEALTH AND SAFETY

It is recommended to wear gloves and glasses while applying Finish Filler. Always wear a dust mask when sanding.

Dispose of unused product and packaging responsibly at your local waste collection centre.

Preservatives:

Contains 1,2-benzisothiazolin-3-one ; 2-methylisothiazolin-3(2H)-one ; C(M)IT / MIT (3 : 1).

May produce an allergic reaction.

Safety data sheet available at [www.toupret.co.uk](http://www.toupret.co.uk)

The data sheet information, especially the guidelines relevant to the application and final use of the product are provided in good faith and result from Toupret's experience and knowledge of the products.

The product should be used as per the trade practices rules book and in reference to our recommendations.

The information provided is relevant to applications processed at a temperature of 20°C, a relative humidity of 50% and on average absorbency substrates.

The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions.



\* Information on the emission level of volatile substances into indoor air, presenting a risk of toxicity by inhalation, on a scale from A+ (very low emissions) to C (high emissions).