METAL CORNER TAPE

REINFORCED METAL CORNER TAPE FOR PLASTERBOARD JOINTING

- CENTRAL GROOVE FOR EASE OF FOLDING
- RESISTS BENDING
- REINFORCED WITH METAL STRIPS
- 51mm x 30m



METAL CORNER TAPE WIDTH: 51mm LENGTH: 30m	
Reference 1.4. March 1.4. Ma	Perint Concernance
Source train a construction of the constr	3 #178310#022535#
DE TOUPRET (UK) LIMITED CONTAL BUSINESS CINITIE EU INITI S 20 ARTON ROMO SUIT AND THE STATUS TOUPRET CONTACT AND THE STATUS SUIT AND THE STATUS WWW TO URBERT CON UK WWW TO URBERT CON UK	

TOUPRET

PURPOSE

For reinforcing internal and external corners in plasterboard jointing.

SUBSTRATES

Metal Corner Tape can be applied to any tapered or butted plasterboard.

OVERCOATING

Metal Corner Tape can be covered with any type of filler, paint or wall covering.

PHYSICAL AND TECHNICAL FEATURES

• Metal Corner Tape is a high quality paper joint tape strengthened with two corrosion-resistant electro-galvanised steel strips for the finishing of internal and external angles in drywall construction.

- Thickness (mm): 0.28mm (+/- 0.0.02mm).
- Width: 11.0mm (+/- 0.10 mm).
- Corrosion resistance: Min. 48 h at stage 4 (afnor X41002 Film A91020).
- Paper weight: 138g/m² (+/- 4%).
- Length: 30m.
- Width: 51mm (+/- 1 mm.).
- Colour: off-white.

USE AND STORAGE CONDITIONS

- Application tools: filling knife.
- Preservation: store in a cool dry place away from humidity.

PACKAGING

Box: contains one 30m x 51mm roll.

RECOMMENDATIONS AND CARE FOR USE

1- Clean the wall, cut the length you need and apply joint filler to a depth of about 3mm (1/8"), covering both sides of the corner at the same time.

2- Fold the tape in the centre, with the metal part facing the wall, and embed firmly into the joint filler.

Remove any excess filler and leave to dry.

2

3- After the first coat is dry, lightly sand the surface.

4- Apply the finishing coat and feather out 100mm beyond the first coat on either side of the board.

Leave to dry and lightly sand, as necessary.

SUBSTRATES PREPARATION

Substrates to be prepared as per the current trade practices. Substrates must be hard, cohesive, clean, sound and dry.

NORMATIVE DOCUMENTS TO BE REFERRED TO

• NF EN 13963 : 2014 - Jointing materials for gypsum boards.

• BS EN 13963 : 2014 - Jointing materials for gypsum boards.

• DTU 25.41 (NFP 72-203-1) Building works - Gypsum plasterboard works - Gypsum wallboards.

HEALTH AND SAFETY

• The data sheet information, especially the guidelines relevant to the application and final use of the product are provided in good faith and result from Toupret's experience and knowledge of the products.

The product should be used as per the trade practices rules book and in reference to our recommendations.



*Information on the emission level of volatile substances into indoor air, presenting a risk of toxicity by inhalation, on a scale from A+ (very low emissions) to C (high emissions).

