

TX230

EXTERIOR FINISHING SURFACER

- ◆ ALL SUBSTRATES
- ◆ IDEAL ON FAÇADES TO BEAUTIFY FINISHING COATINGS
- ◆ ADHERES ON ALL SUBSTRATES EVEN ON TILES
- ◆ EXCELLENT WATER RESISTANT PROPERTIES
- ◆ READY-MIXED



PURPOSE

Ready to use all substrates finishing surfacer, exterior and interior use, manual application. Recommended externally for façade application and internally in damp rooms (kitchens, bathrooms,...) and in renovation to obliterate ceramic tiles.

SUBSTRATES

TX230 can be applied to :

Very smooth and flexible substrates, tiles, cement, plasterboard, primed wood gypsum plaster, concrete, polystyrene, cork, drywall lining, plastic coverings and old painted surfaces.

OVERCOATING

TX230 can be coated over by any type of paint, excepted polyurethane and sovente-based epoxy paints.

PHYSICAL AND TECHNICAL FEATURES

TX230 : filler in paste form for exterior and interior use, made of mineral and synthetic resin.

- Characterization (NFT 36-005): Family IV - Class 4b.
- Codification (EN 16566): $G_3S_2V_0W_0A_0C_0R_5$
- Mixing rate: ready to use.
- Application thickness: up to 3mm per coat.
- Coverage: 1.7 kg / m² / mm.
- Setting time: second coat as soon as the filler is hard and dry to the touch.
- Overcoating: after completely dry.
- Colour: bright beige.
- Adhesion: filler/substrate (EN 16566): > 0.8 Mpa.

USE AND STORAGE CONDITIONS

- Application tools: with trowel or smoothing blade.
- Tools cleaning: with water.
- Preservation: Toupret products are designed for high performance and are guaranteed for 12 months from purchase when used as intended. If the product is found to be faulty within the guarantee period, we will arrange a replacement on proof of purchase. Product should be kept in its original sealed packaging and stored away from sunlight and frost.

PACKAGING

- Bucket of 25 kg.

RECOMMENDATIONS AND CARE FOR USE

- Do not apply under a temperature below 5°C and above 35°C nor under a hygrometry rate over 80%.
- Do not apply on overheated surfaces.
- Do not apply on damp substrates.
- Before sticking any wall coating on a flexible substrate coated or filled with TX230, wait a minimum of one week for the product to fully dry and harden. Proceed with a preliminary test.
- If necessary, rub down as soon as the filler is dry (TX230 is rich in resin and its hardness increases with time).
- On ceramic tiles, proceed in 2 coats with a thin coat at first to allow quick drying.

SUBSTRATES PREPARATION

Substrates to be prepared as per the current trade practices. Substrates must be hard, cohesive, clean, sound and dry.

NORMATIVE DOCUMENTS TO BE REFERRED TO

- NFT 16566: Coating Fillers for interior and/or exterior works.
- NFT 36-005: Characterization of paint products.
- DTU 59.1 (NFP 74-201): Building paint works.
- DTU 59.4 (NFP 74-204): wall papers and wall coverings processing.
- DTU 42.1 (NFP 84-404) : Façades renovation with polymer-based waterproofing coatings.

HEALTH AND SAFETY

It is recommended to wear a dust mask when sanding. It is recommended to wear protective gloves and eye protection during product application. Dispose of unused product and packaging responsibly at your local waste collection centre.

- Very low VOC emissions : < 0,01 %.
- Safety data sheets available on toupret.com.
- No danger tag.

The data sheet information, especially the guidelines relevant to the application and final use of TX230 is provided in good faith and result from TOUPRET's experience and knowledge of the products.

The product should be used as per the trade practices rules book and in reference to our recommendations.

The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions.

KASSA'A PAINTS GROUP
COLOURTEK Bldg

PO BOX 14-5592 MSAYTBEH STREET – BEIRUT – LEBANON
Tel : +961 1 305649 -306966- 303414 E-mail : toupretme@toupret.com

Official distributor :

ATLANTIS BUILDING MATERIALS TRADING (LLC)
PO BOX 214873 DUBAI UNITED ARAB EMIRATES
Tel : +97143405648 / +971558938809 Fax: +97143405649
E-mail: info@atlantis4arch.ae

TOUPRET
FILLERS FOR PROFESSIONALS